

Erratum to “Photoenzymatic RAFT Emulsion Polymerization with Oxygen Tolerance”

Ruo-Yu Li^{a,c} and Ze-Sheng An^{a,b*}

^a State Key Laboratory of Supramolecular Structure and Materials, College of Chemistry, Jilin University, Changchun 130012, China

^b Key Laboratory for Molecular Enzymology and Engineering of Ministry of Education, School of Life Sciences, Jilin University, Changchun 130012, China

^c Institute of Nanochemistry and Nanobiology, College of Environmental and Chemical Engineering, Shanghai University, Shanghai 200444, China

Erratum to *Chinese J. Polym. Sci.* 2021, 39, 1138–1145. DOI: [10.1007/s10118-021-2556-5](https://doi.org/10.1007/s10118-021-2556-5)

Citation: Li, R. Y.; An, Z. S. Erratum to “photoenzymatic RAFT emulsion polymerization with oxygen tolerance”. *Chinese J. Polym. Sci.* 2024, 42, 558.

The authors regret that the name of the polymers in Table S3 was incorrectly written in the original electronic supplementary information (ESI). The corrected version of Table S3 is provided below. Additional text corrections are not needed. The corrections do not change the conclusions of the original study. The authors apologize for any inconvenience caused.

Table S3 Summary of block copolymers synthesized *via* sequential surfactant-free photoenzymatic RAFT emulsion polymerizations.

Entry	Polymer	Conv. (%)	$M_{n,th}$ (kg/mol)	$M_{n,GPC}$ (kg/mol)	$\bar{D}$
1	PDMA ₃₀ - <i>b</i> -PMA ₅₀₀	>99	45.2	47.2	1.18
	PDMA ₃₀ - <i>b</i> -PMA ₅₀₀ - <i>b</i> -PMA ₁₀₀₀	>99	129.3	133.7	1.25
2	PDMA ₃₀ - <i>b</i> -PMA ₁₀₀₀	>99	87.3	82.1	1.17
	PDMA ₃₀ - <i>b</i> -PMA ₁₀₀₀ - <i>b</i> -PMA ₁₀₀₀	>99	171.4	198.2	1.28

Polymerization conditions: no prior deoxygenation, [glucose]₀=10 mmol/L, [GOx]₀=0.75 μmol/L, PBS buffer (20 mmol/L, pH 5.8), violet LED light (405 nm, 0.4 mW/cm²), room temperature, 6 h for each block. Monomer conversion determined by ¹H-NMR spectroscopy in DMSO-*d*₆.

* Corresponding author, E-mail: anzesheng@jlu.edu.cn